



# EPOCAST 36<sup>®</sup>

Product of the **ITW** Performance Polymers

## Description

**Epocast 36<sup>®</sup>** is a special, two-component pourable chocking compound enriched with high-grade fillers. Modern manufacturing methods, filling and testing systems guarantee constant compliance with the physical and chemical properties required for **Epocast 36<sup>®</sup>** by Classification Societies and other institution. **Epocast 36<sup>®</sup>** resin chocks are easy to use and offer a cost-effective alternative for conventional methods

## Application

**Epocast 36<sup>®</sup>** is engineered for use as suitable replacement for steel chocks when mounting main engines and auxiliary gears, compressors, pumps, tiling machines, paper presses, thrust and support bearings, etc. under service temperatures up to 80°C and maximum surface load of 5.0 N/mm<sup>2</sup>.

## Mechanical proprieties

**Epocast 36<sup>®</sup>** is simply to use, compensates all irregularities of surfaces in this way don't requires machining of the foundation. **Epocast 36<sup>®</sup>** allows to pour chocks up to 80 mm thick depending on the ambient temperature. It is characterized by high compressive and impact strength and chemical resistance; reduces noise and vibrations. **Epocast 36<sup>®</sup>** protects from crack corrosion.



**MARINE SERVICE JAROSZEWICZ S.C.**

ul. Bielańska 23, 70-703 Szczecin

tel.: +48 91 4606624

<http://www.epyresin.eu>, e-mail: [msj@epyresin.eu](mailto:msj@epyresin.eu)

## Mechanical proprieties

|  |  |             |
|--|--|-------------|
| <b>Coefficient of linear thermal expansion</b> | 43,8 x 10 <sup>-6</sup> 1/K  |             |
| <b>Linear shrinkage</b>                        | 15 x 10 <sup>-4</sup> mm/mm  | ASTM D-2566 |
| <b>Compressive strength</b>                    | 164 N/mm <sup>2</sup>  | ASTM D-695  |
| <b>Compressive modulus of elasticity</b>       | 5610 N/mm <sup>2</sup>   | ASTM D-695  |
| <b>Tensile strength</b>                        | 49,4 N/mm <sup>2</sup>   | ASTM D-638  |
| <b>Elastic shear modulus</b>                   | 2360 N/mm <sup>2</sup>   |             |
| <b>Izoda impact</b>                            | 17,2 J/m   | ASTM D-256  |
| <b>Hardness - Barcol</b>                       | 55 °Barcola  | ASTM D-2583 |
| <b>Friction coefficient</b>                    | 0,57   |             |
| <b>Specific gravity</b>                        | 1,64 kg/dm <sup>3</sup>  |             |
| <b>Pot life</b>                                | 30 min. @ 25 °C<br>10 min. @ 50 °C   |             |
| <b>Cure time</b>                               | 48 hours @ 16 °C<br>28 hours @ 21 °C   |             |
| <b>Creep in 70 °C</b>                          | 0,013 mm @ 3,4 N/mm <sup>2</sup><br>0,016 mm @ 6,9 N/mm <sup>2</sup><br>0,020 mm @ 13,8 N/mm <sup>2</sup><br>0,030 mm @ 27,6 N/mm <sup>2</sup> | ASTM D-621  |

## Market form

|                   |  |
|-------------------|--|
| <b>Metal cans</b> | 3,2 kg / 2,0 dm <sup>3</sup><br>6,4 kg / 4,0 dm <sup>3</sup> |
|-------------------|--|



**MARINE SERVICE JAROSZEWICZ S.C.**

ul. Bielańska 23, 70-703 Szczecin

tel.: +48 91 4606624

<http://www.epyresin.eu>, e-mail: [msj@epyresin.eu](mailto:msj@epyresin.eu)